Format No: CP/TF/01

# TEST REPORT OF CEMENT CONCRETE CUBES

**Lab ID** : **CP-2021-01-13-45** **Date: 05/08/2020**

**Customer** : Assistant Executive Engineer, Vidyaranyapura Sub Division, BBMP, Bangalore.

**Address** : Vidyaranyapura Sub Division, BBMP, Bangalore.

**Project Name** : "Improvements to Roads and Drains at G Krishna Murty Layout Mutturayaswamy Layout G K Muniyappa Garden in Ward No 10 Doddabommasandra Vidyaranyapura Sub Division."

**Agency** : Sri.Abbu Sambasiva Reddy, No: 1B3, Sree Arcade Layout, 4th Block Doddabommasandra, Vidyaranyapura Post, Bangalore-97.

**Customer's Reference** : BBMP/EE/BTP/WO/45/2020-21

**Source of Sample** : Sample supplied by Agency

**Sample Condition** : Satisfactory

**Date of Receipt** : 31-07-20

**Customer ID** : Cement Concrete Pavement

**Sample Type /Size** : 150X150X150 mm

**Sample grade/Age** : M30 / 7 Days Compressive Strength

**Reference to BIS codes** : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

**Date of test** : 05/08/2020

| Sl. No. | Identification Mark | Grade of concrete | Date of Casting | Date of Testing | Dimension of the Specimen (mm) | Cross sectional area (Sq.mm) | Weight of the sample (kg) | Failure Load (KN) | Compressive strength ($N/mm^2$) | Average Compressive Strength ($N/mm^2$) |
|---|---|---|---|---|---|---|---|---|---|---|
| 1 | Cement Concrete Pavement | M30 | 29/07/2020 | 05/08/2020 | 151.36 X 151.14 X 151.89 | 22878 | 8.998 | 581.3 | 25.4 | 25.3 |
| 2 | Cement Concrete Pavement | M30 | 29/07/2020 | 05/08/2020 | 151.46 X 151.39 X 149.80 | 22930 | 8.488 | 600.1 | 26.2 | |
| 3 | Cement Concrete Pavement | M30 | 29/07/2020 | 05/08/2020 | 149.24 X 150.38 X 151.30 | 22443 | 8.245 | 548.8 | 24.5 | |

* The results obtained are satisfactory as per standard requirements.

**Note:**

The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 30 days from the date of issue of test certificate

Suvetha.N.K
AE W 10

CIVIL PRO BANGALORE Sig Date

FOR CIVIL Pro.

R RUDRAPRASAD
Authorized Signatory
**Technical Manager**


****End of Report****

Format No: CP/TF/01

# TEST REPORT OF CEMENT CONCRETE CUBES

| | | |
|---|---|---|
| **Lab ID** | : | **CP-2021-01-13-45** **Date: 26/08/2020** |
| **Customer** | : | Assistant Executive Engineer, Vidyaranyapura Sub Division, BBMP, Bangalore. |
| **Address** | : | Vidyaranyapura Sub Division, BBMP, Bangalore. |
| **Project Name** | : | "Improvements to Roads and Drains at G Krishna Murty Layout Mutturayaswamy Layout G K Muniyappa Garden in Ward No 10 Doddabommasandra Vidyaranyapura Sub Division." |
| **Agency** | : | Sri.Abbu Sambasiva Reddy, No: 1B3, Sree Arcade Layout, 4th Block Doddabommasandra, Vidyaranyapura Post, Bangalore-97. |
| **Customer's Reference** | : | BBMP/EE/BTP/WO/45/2020-21 |
| **Source of Sample** | : | Sample supplied by Agency |
| **Sample Condition** | : | Satisfactory |
| **Date of Receipt** | : | 31-07-20 |
| **Customer ID** | : | Cement Concrete Pavement |
| **Sample Type /Size** | : | 150X150X150 mm |
| **Sample grade/Age** | : | M30 / 28 Days Compressive Strength |
| **Reference to BIS codes** | : | IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5 |
| **Date of test** | : | 26/08/2020 |

| Sl. No. | Identification Mark | Grade of concrete | Date of Casting | Date of Testing | Dimension of the Specimen (mm) | Cross sectional area (Sq.mm) | Weight of the sample (kg) | Failure Load (KN) | Compressive strength ($N/mm^2$) | Average Compressive Strength ($N/mm^2$) |
|---|---|---|---|---|---|---|---|---|---|---|
| 1 | Cement Concrete Pavement | M30 | 29/07/2020 | 26/08/2020 | 150.37 X 151.68 X 151.93 | 22808 | **8.571** | 755.3 | 33.1 | 33.1 |
| 2 | Cement Concrete Pavement | M30 | 29/07/2020 | 26/08/2020 | 149.01 X 151.43 X 150.32 | 22565 | **8.375** | 727.3 | 32.2 | |
| 3 | Cement Concrete Pavement | M30 | 29/07/2020 | 26/08/2020 | 151.50 X 149.77 X 151.70 | 22690 | **8.433** | 771.4 | 34.0 | |

* The results obtained are satisfactory as per standard requirements.

**Note:**

The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 30 days from the date of issue of test certificate

Sreenivasa. N K
AE W10

Assistant Executive Engineer
Vidyaranyapura Sub Division
BBMP, Bangalore-97

CIVIL PRO BANGALORE Sig. Date

**FOR CIVIL Pro.**

**R RUDRAPRASAD**
Authorized Signatory
**Technical Manager**


****End of Report****

Format No: CP/TF/01

# TEST REPORT OF CEMENT CONCRETE CUBES

**Lab ID** : **CP-2021-01-13-45** **Date: 05/08/2020**

**Customer** : Assistant Executive Engineer, Vidyaranyapura Sub Division, BBMP, Bangalore.

**Address** : Vidyaranyapura Sub Division, BBMP, Bangalore.

**Project Name** : "Improvements to Roads and Drains at G Krishna Murty Layout Mutturayaswamy Layout G K Muniyappa Garden in Ward No 10 Doddabommasandra Vidyaranyapura Sub Division."

**Agency** : Sri.Abbu Sambasiva Reddy, No: 1B3, Sree Arcade Layout, 4th Block Doddabommasandra, Vidyaranyapura Post, Bangalore-97.

**Customer's Reference** : BBMP/EE/BTP/WO/45/2020-21

**Source of Sample** : Sample supplied by Agency

**Sample Condition** : Satisfactory

**Date of Receipt** : 31-07-20

**Customer ID** : Cement Concrete Pavement

**Sample Type /Size** : 150X150X150 mm

**Sample grade/Age** : M30 / 7 Days Compressive Strength

**Reference to BIS codes** : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

**Date of test** : 05/08/2020

| Sl. No. | Identification Mark | Grade of concrete | Date of Casting | Date of Testing | Dimension of the Specimen (mm) | Cross sectional area (Sq.mm) | Weight of the sample (kg) | Failure Load (KN) | Compressive strength ($N/mm^2$) | Average Compressive Strength ($N/mm^2$) |
|---|---|---|---|---|---|---|---|---|---|---|
| 1 | Cement Concrete Pavement | M30 | 29/07/2020 | 05/08/2020 | 149.95 X 150.79 X 150.78 | 22611 | **8.998** | 578.6 | 25.6 | 25.5 |
| 2 | Cement Concrete Pavement | M30 | 29/07/2020 | 05/08/2020 | 149.95 X 151.85 X 149.93 | 22770 | **8.488** | 608.3 | 26.7 | |
| 3 | Cement Concrete Pavement | M30 | 29/07/2020 | 05/08/2020 | 150.85 X 150.65 X 150.30 | 22726 | **8.245** | 550.4 | 24.2 | |

* The results obtained are satisfactory as per standard requirements.

**Note:**

The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 30 days from the date of issue of test certificate

Suvitha. NK
AE W10

CIVIL Pro Sig. Date. BANGALORE

**FOR CIVIL Pro.**

**R RUDRAPRASAD**
Authorized Signatory
**Technical Manager**


****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL | GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES

Format No: CP/TF/01

# TEST REPORT OF CEMENT CONCRETE CUBES

**Lab ID** : **CP-2021-01-13-45** **Date: 26/08/2020**

**Customer** : Assistant Executive Engineer, Vidyaranyapura Sub Division, BBMP, Bangalore.

**Address** : Vidyaranyapura Sub Division, BBMP, Bangalore.

**Project Name** : "Improvements to Roads and Drains at G Krishna Murty Layout Mutturayaswamy Layout G K Muniyappa Garden in Ward No 10 Doddabommasandra Vidyaranyapura Sub Division."

**Agency** : Sri.Abbu Sambasiva Reddy, No: 1B3, Sree Arcade Layout, 4th Block Doddabommasandra, Vidyaranyapura Post, Bangalore-97.

**Customer's Reference** : BBMP/EE/BTP/WO/45/2020-21

**Source of Sample** : Sample supplied by Agency

**Sample Condition** : Satisfactory

**Date of Receipt** : 31-07-20

**Customer ID** : Cement Concrete Pavement

**Sample Type /Size** : 150X150X150 mm

**Sample grade/Age** : M30 / 28 Days Compressive Strength

**Reference to BIS codes** : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

**Date of test** : 26/08/2020

| Sl. No. | Identification Mark | Grade of concrete | Date of Casting | Date of Testing | Dimension of the Specimen (mm) | Cross sectional area (Sq.mm) | Weight of the sample (kg) | Failure Load (KN) | Compressive strength ($N/mm^2$) | Average Compressive Strength ($N/mm^2$) |
|---|---|---|---|---|---|---|---|---|---|---|
| 1 | Cement Concrete Pavement | M30 | 29/07/2020 | 26/08/2020 | 151.24 X 151.63 X 151.98 | 22933 | 8.571 | 764.3 | 33.3 | 33.3 |
| 2 | Cement Concrete Pavement | M30 | 29/07/2020 | 26/08/2020 | 151.72 X 149.01 X 151.27 | 22607 | 8.375 | 745.7 | 33.0 | |
| 3 | Cement Concrete Pavement | M30 | 29/07/2020 | 26/08/2020 | 151.68 X 149.30 X 151.92 | 22646 | 8.433 | 763.3 | 33.7 | |

* The results obtained are satisfactory as per standard requirements.

**Note:**

The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 30 days from the date of issue of test certificate

Sunitha-NK
AE W10

CIVIL Pro Sig. Date BANGALORE

FOR CIVIL Pro.
R RUDRAPRASAD
Authorized Signatory
Technical Manager


****End of Report****

## QC ABSTRACT

**NAME OF WORK:** "Improvements to Roads and Drains at G Krishna Murty Layout Mutturayaswamy Layout G K Muniyappa Garden in Ward No 10 Doddabommasandra Vidyaranyapura Sub Division."

| SL NO | Item Of Work | Name of Test | Frequency of Test/Quantity | Executed Quantity | Number of Tests Required | Number of Tests Conducted |
|---|---|---|---|---|---|---|
| | | **Materials** | | | | |
| 1 | Cement | Fineness by dry sieving | One Test | | 1 | 1 |
| | | Finess by Air permeablity method | One Test | | 1 | 1 |
| | | Density | One Test | | 1 | 1 |
| | | Standard Consistency | One Test | | 1 | 1 |
| | | Initial Setting time | One Test | | 1 | 1 |
| | | Final Setting time | One Test | | 1 | 1 |
| | | Soundness (Le Chatelier's Method) | One Test | | 1 | 1 |
| | | Compressive Strength | One Test | | 1 | 1 |
| 2 | Coarse aggregate(40 mm down size) | SIEVE ANALYSIS | One Test | | 1 | 1 |
| | | Flakiness Index | One Test | | 1 | 1 |
| | | Elongation Index | One Test | | 1 | 1 |
| | | Specific Gravity | One Test | | 1 | 1 |
| | | Bulk Density(Loose) | One Test | | 1 | 1 |
| | | Bulk Density(Compacted) | One Test | | 1 | 1 |
| | | Water Absorption | One Test | | 1 | 1 |
| 3 | Coarse aggregate(20 mm down size) | SIEVE ANALYSIS | One Test | | 1 | 1 |
| | | Flakiness Index | One Test | | 1 | 1 |
| | | Elongation Index | One Test | | 1 | 1 |
| | | Specific Gravity | One Test | | 1 | 1 |
| | | Bulk Density(Loose) | One Test | | 1 | 1 |
| | | Bulk Density(Compacted) | One Test | | 1 | 1 |
| | | Water Absorption | One Test | | 1 | 1 |
| | | Aggregate crushing Value | One Test | | 1 | 1 |
| | | Aggregate Impact Value | One Test | | 1 | 1 |
| 4 | Fine aggregate | SIEVE ANALYSIS | One Test | | 1 | 1 |
| | | Water Absorption | One Test | | 1 | 1 |
| | | Specific Gravity | One Test | | 1 | 1 |
| | | Material finer than 75 micron | One Test | | 1 | 1 |
| 5 | Cement Concrete Pavemet (M30) | Compressive Strength(7days and 28days) | 7 set /151-200 cum | 185.35 | 14 | 14 |

Sunitha.NK
AE W10

Assistant Executive Engineer
Vidyaranyapura Sub Division
BBMP, Bangalore - 97

Format No: CP/TF/01

## TEST REPORT OF PHYSICAL PROPERTIES OF CEMENT - 53 Grade

| | | |
|---|---|---|
| **Lab ID** | : | **CP-2021-01-13-45** **Date: 25-07-20** |
| **Customer** | : | Assistant Executive Engineer, Vidyaranyapura Sub Division, BBMP, Bangalore. |
| **Address** | : | Vidyaranyapura Sub Division, BBMP, Bangalore. |
| **Project Name** | : | "Improvements to Roads and Drains at G Krishna Murty Layout Mutturayaswamy Layout G K Muniyappa Garden in Ward No 10 Doddabommasandra Vidyaranyapura Sub Division." |
| **Agency** | : | Sri.Abbu Sambasiva Reddy, No: 1B3, Sree Arcade Layout, 4th Block Doddabommasandra, Vidyaranyapura Post, Bangalore-97. |
| **Customer's Reference** | : | BBMP/EE/BTP/WO/45/2020-21 |
| **Source of Sample** | : | Sample supplied by Agency |
| **Sample Condition** | : | Satisfactory |
| **Date of Receipt** | : | 22-07-20 |
| **Sample Type** | : | Birla Super 53grade |
| **Reference to BIS codes** | : | IS 12269 : 2013, 53 Grade Ordinary Portland cement Specification ,<br>IS 4031 (Part 1,2 3,4,5, 6,11):1988<br>IS 4031 Part 1 DETERMINATION OF FINENESS BY DRY SIEVING, Clause 4.4<br>IS 4031 Part 2, Determination of Fineness by Blaine Air Permeability Method, Clause 5<br>IS 4031 Part 3, Determination of Soundness, Clause 5,Clause 6<br>IS 4031 Part 4, Determination of Consistency of Standard Cement Paste, Clause 5<br>IS 4031 Part 5, Determination of Initial & Final Setting Time, Clause 5<br>IS 4031 Part 11,DETERMINATION OF DENSITY , Clause 6 |
| **Date of test** | : | 23-07-20 |
| **Environmental Conditions during test** | : | Temperature: 26°C<br>Humidity: 72% |

| Sl.No. | Physical properties | Results | Requirement as per IS 12269: 2013 |
|---|---|---|---|
| 1 | Fineness by dry sieving (%) | 1.63 | _ |
| 2 | Finess by Air permeablity method ($m^2$/kg,Min) | 298.4 | 225$m^2$/kg, Min |
| 3 | Density (gm/cc) | 3.12 | _ |
| 4 | Standard Consistency (%) | 29.0% | Not specified |
| 5 | Initial Setting time | 140 minutes | Not less than 30 minutes |
| 6 | Final Setting time | 250 minutes | Not more than 600 minutes |
| 7 | Soundness (Le Chatelier's Method) | 1.0mm | Not more than 10 mm |

* The results obtained are satisfactory as per standard requirements.

**Note:**

The results pertain to the samples received and tested.

All information furnished by Customer/Representative

Any correction in the report will make this report invalid

This report without prior written approval should not be reproduced or published in full or part.

Samples will be disposed after 30 days from the date of issue of test certificate

Sweetha. N.K
AE W10

CIVIL Pro BANGALORE Sig. Date

**FOR CIVIL Pro.**

**R RUDRAPRASAD**
Authorized Signatory
**Technical Manager**



****End of Report****

Format No: CP/TF/01

## TEST REPORT OF PHYSICAL PROPERTIES OF CEMENT - 53 Grade

| | | |
|---|---|---|
| **Lab ID** | : | **CP-2021-01-13-45** **Date: 20-08-20** |
| **Customer** | : | Assistant Executive Engineer, Vidyaranyapura Sub Division, BBMP, Bangalore. |
| **Address** | : | Vidyaranyapura Sub Division, BBMP, Bangalore. |
| **Project Name** | : | "Improvements to Roads and Drains at G Krishna Murty Layout Mutturayaswamy Layout G K Muniyappa Garden in Ward No 10 Doddabommasandra Vidyaranyapura Sub Division." |
| **Agency** | : | Sri.Abbu Sambasiva Reddy, No: 1B3, Sree Arcade Layout, 4th Block Doddabommasandra, Vidyaranyapura Post, Bangalore-97. |
| **Customer's Reference** | : | BBMP/EE/BTP/WO/45/2020-21 |
| **Source of Sample** | : | Sample supplied by Agency |
| **Sample Condition** | : | Satisfactory |
| **Date of Receipt** | : | 22-07-20 |
| **Sample Type** | : | Birla Super 53grade |
| **Reference to BIS codes** | : | IS 12269 : 2013, 53 Grade Ordinary Portland cement Specification ,<br>IS 4031 Part 4, Determination of Consistency of Standard Cement Paste, Clause 5<br>IS 4031 Part 6, Determination of Compressive Strength, Clause 6 |
| **Date of test** | : | 23-07-20 |
| **Environmental Conditions during test** | : | Temperature: 26°C<br>Humidity: 72% |

| **Compressive Strength** | | | |
|---|---|---|---|
| **Sl.No.** | **Physical properties** | **Results** | **Requirement as per IS 12269: 2013** |
| 1 | 3 Days | 28.5N/mm$^2$ | Not less than 27 N/mm$^2$ |
| 2 | 7 Days | 39.0N/mm$^2$ | Not less than 37 N/mm$^2$ |
| 3 | 28 Days | 58.5N/mm$^2$ | Not less than 53 N/mm$^2$ |

* The results obtained are satisfactory as per standard requirements.

**Note:**

The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 30 days from the date of issue of test certificate

Sweetha. NK
AE WIO

CIVIL PRO BANGALORE Sig. Date

**FOR CIVIL Pro.**
**R RUDRAPRASAD**
Authorized Signatory
**Technical Manager**


****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL | GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES |

Format No: CP/TF/01

## TEST REPORT ON COARSE AGGREGATES

| | | |
|---|---|---|
| **Lab ID** | : | **CP-2021-01-13-45** **Date: 25-07-20** |
| **Customer** | : | Assistant Executive Engineer, Vidyaranyapura Sub Division, BBMP, Bangalore. |
| **Address** | : | Vidyaranyapura Sub Division, BBMP, Bangalore. |
| **Project Name** | : | "Improvements to Roads and Drains at G Krishna Murty Layout Mutturayaswamy Layout G K Muniyappa Garden in Ward No 10 Doddabommasandra Vidyaranyapura Sub Division." |
| **Agency** | : | Sri.Abbu Sambasiva Reddy, No: 1B3, Sree Arcade Layout, 4th Block Doddabommasandra, Vidyaranyapura Post, Bangalore-97. |
| **Customer's Reference** | : | BBMP/EE/BTP/WO/45/2020-21 |
| **Source of Sample** | : | Sample supplied by Agency |
| **Sample condition** | : | Satisfactory |
| **Date of Receipt** | : | 22-07-20 |
| **Sample Type** | : | 40mm down size coarse aggregate |
| **Reference to BIS codes** | : | IS: 383:2016 (Specification for Coarse and fine Aggregates )<br>IS: 2386 :1963(Part - 1,3,4) RA2011<br>IS 2386 Part 1: Particle Size and Shape<br>IS 2386 Part 3: Specific gravity, Density, Voids,Water Absorption<br>IS 2386 Part 4: Mechanical Properties |
| **Date of test** | : | 22-07-20 |

**SIEVE ANALYSIS (PARTICLE SIZE DISTRIBUTION) OF 40MM DOWN COARSE AGGREGATE:**

**Total weight taken : 15000 grams**

| Sample No. | Sieve No. | Weight Retained in gms | Cumulative Weight Retained in gms | % Cumulative Weight Retained | % Passing | Required as per IS 383:2016 |
|---|---|---|---|---|---|---|
| 1 | 80 mm | 0 | 0 | 0.0 | 100 | 100 |
| 2 | 40 mm | 589 | 589 | 3.9 | 96.1 | 90-100 |
| 3 | 20 mm | 4898 | 5487 | 36.6 | 63.4 | 30-70 |
| 4 | 10 mm | 7143 | 12630 | 84.2 | 15.8 | 10-35 |
| 5 | 4.75 mm | 2118 | 14748 | 98.3 | 1.7 | 0-5 |
| 6 | Pan | 252 | 15000 | 100.0 | 0 | --- |

Geetha.NK
AE W16



CIVIL PRO Sig Date BANGALORE

Format No: CP/TF/01

## TEST REPORT ON COARSE AGGREGATES

**Lab ID** : **CP-2021-01-13-45** **Date: 25-07-20**

**PHYSICAL PROPERTIES**

| Sl.no | Tests | Result | Requirements as per IS:383-2016 |
|---|---|---|---|
| 1 | Flakiness Index(%) | 9.2 | Combined Flakiness & Elongation Index Shall not Exceed 40% for Uncrushed & Crushed Aggregate |
| 2 | Elongation Index(%) | 10.4 | |
| 3 | Specific Gravity | 2.67 | _ |
| 4 | Bulk Density(Loose) (Kg/l) | 1.42 | _ |
| 5 | Bulk Density(Compacted) (Kg/l) | 1.47 | _ |
| 6 | Water Absorption(%) | 0.38 | _ |

* The results obtained are satisfactory as per standard requirements.

**Note:**

The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 30 days from the date of issue of test certificate

**FOR CIVIL Pro.**

**R RUDRAPRASAD**
Authorized Signatory
**Technical Manager**

CIVIL Pro Sig Date BANGALORE



****End of Report****

Sunitha. NK
AEN 10

Assistant Executive Engineer
Vidyaranyapura Sub Division
BBMP, Bangalore - 97

Format No: CP/TF/01

## TEST REPORT ON COARSE AGGREGATES

| | | |
|---|---|---|
| **Lab ID** | : | **CP-2021-01-13-45** **Date: 24-07-20** |
| **Customer** | : | Assistant Executive Engineer, Vidyaranyapura Sub Division, BBMP, Bangalore. |
| **Address** | : | Vidyaranyapura Sub Division, BBMP, Bangalore. |
| **Project Name** | : | "Improvements to Roads and Drains at G Krishna Murty Layout Mutturayaswamy Layout G K Muniyappa Garden in Ward No 10 Doddabommasandra Vidyaranyapura Sub Division." |
| **Agency** | : | Sri.Abbu Sambasiva Reddy, No: 1B3, Sree Arcade Layout, 4th Block Doddabommasandra, Vidyaranyapura Post, Bangalore-97. |
| **Customer Reference** | : | BBMP/EE/BTP/WO/45/2020-21 |
| **Source of Sample** | : | Sample supplied by Agency |
| **Sample Condition** | : | Satisfactory |
| **Date of Receipt** | : | 22-07-20 |
| **Sample Type/ Size** | : | 20mm down size coarse aggregate |
| **Reference to BIS codes** | : | IS: 383:2016 (Specification for Coarse and fine Aggregates )<br>IS: 2386 :1963(Part - 1,3,4) RA2011<br>IS 2386 Part 1: Particle Size and Shape<br>IS 2386 Part 3: Specific gravity, Density, Voids,Water Absorption<br>IS 2386 Part 4: Mechanical Properties |
| **Date of test** | : | 22-07-20 |

**SIEVE ANALYSIS (PARTICLE SIZE DISTRIBUTION) OF 20MM DOWN COARSE AGGREGATE:**

**Total weight taken** : **5000** **grams**

| Sample No. | Sieve No. | Weight Retained in gms | Cumulative Weight Retained in gms | % Cumulative Weight Retained | % Passing | Required as per IS 383:2016 |
|---|---|---|---|---|---|---|
| 1 | 40 mm | 0 | 0 | 0 | 100 | 100 |
| 2 | 20 mm | 198 | 198 | 4.0 | 96.0 | 90-100 |
| 3 | 10 mm | 3150 | 3348 | 67.0 | 33.0 | 25-55 |
| 4 | 4.75 mm | 1457 | 4805 | 96.1 | 3.9 | 0-10 |
| 5 | Pan | 195 | 5000 | 100 | 0 | _ |

Geetha. N.K
AE W10



CIVIL PRO Sig. Date. BANGALORE

Format No: CP/TF/01

## TEST REPORT ON COARSE AGGREGATES

**Lab ID** : **CP-2021-01-13-45** **Date: 24-07-20**

**PHYSICAL PROPERTIES**

| Sl.no | Tests | Result | Requirements as per IS:383-2016 |
|---|---|---|---|
| 1 | Flakiness Index(%) | 11.8 | Combined Flakiness & Elongation Index Shall not Exceed 40% for Uncrushed & Crushed Aggregate |
| 2 | Elongation Index(%) | 12.2 | |
| 3 | Specific Gravity | 2.64 | _ |
| 4 | Bulk Density(Loose) (Kg/l) | 1.44 | _ |
| 5 | Bulk Density(Compacted) (Kg/l) | 1.5 | _ |
| 6 | Water Absorption(%) | 0.27 | _ |
| 7 | Aggregate crushing Value(%) | 22.8 | Max 30% for Aggregates to be used in concrete for wearing Surface, In case Aggregate Crushing Value Exceeds 30% then the test for ten percent fines should be conducted for Aggregates to be used in concrete other than for wearing Surface. |
| 8 | Aggregate Impact Value(%) | 23.6 | 30% for Aggregates to be used in concrete for wearing Surface, 45% for Aggregates to be used in concrete other than for wearing Surface. |

* The results obtained are satisfactory as per standard requirements.

**Note:**

The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 30 days from the date of issue of test certificate

**FOR CIVIL Pro.**

**R RUDRAPRASAD**
Authorized Signatory
**Technical Manager**

Sweetha. NK
AE L10

CIVIL Pro Sig Date BANGALORE


*End of Report*

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL | GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES |

Format No: CP/TF/01

# TEST REPORT OF FINE AGGREGATE

**Lab ID** : **CP-2021-01-13-45** **Date: 24-07-20**

**Customer** : Assistant Executive Engineer, Vidyaranyapura Sub Division, BBMP, Bangalore.

**Address** : Vidyaranyapura Sub Division, BBMP, Bangalore.

**Project Name** : "Improvements to Roads and Drains at G Krishna Murty Layout Mutturayaswamy Layout G K Muniyappa Garden in Ward No 10 Doddabommasandra Vidyaranyapura Sub Division."

**Agency** : Sri.Abbu Sambasiva Reddy, No: 1B3, Sree Arcade Layout, 4th Block Doddabommasandra, Vidyaranyapura Post, Bangalore-97.

**Customer's Reference** : BBMP/EE/BTP/WO/45/2020-21

**Source of Sample** : Sample supplied by Agency

**Sample Condition** : Satisfactory

**Date of Receipt** : 22-07-20

**Sample Type** : Fine Aggregate

**Reference to BIS codes** : IS 383 : 2016 (Specification for Coarse and fine Aggregates)
IS: 2386 :1963(Part - 1, 3) RA2012
IS 2386 Part 1: Particle Size and Shape
IS 2386 Part 3: Specific gravity, Density, Voids,Water Absorption

**Date of test** : 22-07-20

**Total weight taken** : 1000 grams

| Sl.no | Sieve Size | Weight Retained (gms) | Cumulative Weight Retained (gms) | % Cumulative Weight Retained | % Passing | Requirement as per IS 383:2016 | | | |
|---|---|---|---|---|---|---|---|---|---|
| | | | | | | Grading Zone I | Grading Zone II | Grading Zone III | Grading Zone IV |
| 1 | 10 mm | 0 | 0 | 0.0 | 100.0 | 100 | 100 | 100 | 100 |
| 2 | 4.75 mm | 27 | 27 | 2.7 | 97.3 | 90-100 | 90-100 | 90-100 | 95-100 |
| 3 | 2.36 mm | 55 | 82 | 8.2 | 91.8 | 60-95 | 75-100 | 85-100 | 95-100 |
| 4 | 1.18 mm | 239 | 321 | 32.1 | 67.9 | 30-70 | 55-90 | 75-100 | 90-100 |
| 5 | 600 micron | 205 | 526 | 52.6 | 47.4 | 15-34 | 35-59 | 60-79 | 80-100 |
| 6 | 300 micron | 203 | 729 | 72.9 | 27.1 | 5-20 | 8-30 | 12-40 | 15-50 |
| 7 | 150 micron | 191 | 920 | 92.0 | 8.0 | 0-10 | 0-10 | 0-10 | 0-15 |
| 8 | Pan | 80 | 1000 | 100.0 | 0.0 | --- | --- | --- | --- |

**Result :The tested Sample Conforms to Grading Zone II**

Suvetha. N.K
AE L10



CIVIL PRO BANGALORE Sig. Date

# TEST REPORT OF FINE AGGREGATE

**Lab ID** : **CP-2021-01-13-45** **Date: 24-07-20**

**PHYSICAL PROPERTIES**

| Sl.no | Tests | Result | Requirements as per IS 383:2016 |
|---|---|---|---|
| 1 | Water Absorption(%) | 1.5 | – |
| 2 | Specific Gravity | 2.59 | – |
| 3 | Material finer than 75 micron(%) | 6.9 | Uncrushed fine Aggregate Max 3%, Crushed Fine aggregate Max 15%, Mixed Fine aggregate Max 12%, Manufactured Fine aggregate Max 10% |

* The results obtained are satisfactory as per standard requirements.

**Note:**

The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 30 days from the date of issue of test certificate

**FOR CIVIL Pro.**

**R RUDRAPRASAD**
Authorized Signatory
**Technical Manager**

CIVIL Pro Sig. Date. BANGALORE



****End of Report****

Suvetha-NK
AE 2.0

Format No: CP/TF/01

# TEST REPORT OF CEMENT CONCRETE CUBES

**Lab ID** : **CP-2021-01-13-45** **Date: 05/08/2020**

**Customer** : Assistant Executive Engineer, Vidyaranyapura Sub Division, BBMP, Bangalore.

**Address** : Vidyaranyapura Sub Division, BBMP, Bangalore.

**Project Name** : "Improvements to Roads and Drains at G Krishna Murty Layout Mutturayaswamy Layout G K Muniyappa Garden in Ward No 10 Doddabommasandra Vidyaranyapura Sub Division."

**Agency** : Sri.Abbu Sambasiva Reddy, No: 1B3, Sree Arcade Layout, 4th Block Doddabommasandra, Vidyaranyapura Post, Bangalore-97.

**Customer's Reference** : BBMP/EE/BTP/WO/45/2020-21

**Source of Sample** : Sample supplied by Agency

**Sample Condition** : Satisfactory

**Date of Receipt** : 31-07-20

**Customer ID** : Cement Concrete Pavement

**Sample Type /Size** : 150X150X150 mm

**Sample grade/Age** : M30 / 7 Days Compressive Strength

**Reference to BIS codes** : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

**Date of test** : 05/08/2020

| Sl. No. | Identification Mark | Grade of concrete | Date of Casting | Date of Testing | Dimension of the Specimen (mm) | Cross sectional area (Sq.mm) | Weight of the sample (kg) | Failure Load (KN) | Compressive strength ($N/mm^2$) | Average Compressive Strength ($N/mm^2$) |
|---|---|---|---|---|---|---|---|---|---|---|
| 1 | Cement Concrete Pavement | M30 | 29/07/2020 | 05/08/2020 | 150.54 X 149.58 X 150.49 | 22517 | **8.998** | 579.0 | 25.7 | 25.8 |
| 2 | Cement Concrete Pavement | M30 | 29/07/2020 | 05/08/2020 | 150.72 X 149.36 X 151.70 | 22512 | **8.488** | 601.1 | 26.7 | |
| 3 | Cement Concrete Pavement | M30 | 29/07/2020 | 05/08/2020 | 151.84 X 151.26 X 151.09 | 22967 | **8.245** | 572.4 | 24.9 | |

* The results obtained are satisfactory as per standard requirements.

**Note:**

The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 30 days from the date of issue of test certificate

Suvetha. N K
AE L10

31.08.20

CIVIL Pro Sig. Date BANGALORE

**FOR CIVIL Pro.**

**R RUDRAPRASAD**
Authorized Signatory
**Technical Manager**


****End of Report****

Format No: CP/TF/01

# TEST REPORT OF CEMENT CONCRETE CUBES

**Lab ID** : **CP-2021-01-13-45** **Date: 26/08/2020**

**Customer** : Assistant Executive Engineer, Vidyaranyapura Sub Division, BBMP, Bangalore.

**Address** : Vidyaranyapura Sub Division, BBMP, Bangalore.

**Project Name** : "Improvements to Roads and Drains at G Krishna Murty Layout Mutturayaswamy Layout G K Muniyappa Garden in Ward No 10 Doddabommasandra Vidyaranyapura Sub Division."

**Agency** : Sri.Abbu Sambasiva Reddy, No: 1B3, Sree Arcade Layout, 4th Block Doddabommasandra, Vidyaranyapura Post, Bangalore-97.

**Customer's Reference** : BBMP/EE/BTP/WO/45/2020-21

**Source of Sample** : Sample supplied by Agency

**Sample Condition** : Satisfactory

**Date of Receipt** : 31-07-20

**Customer ID** : Cement Concrete Pavement

**Sample Type /Size** : 150X150X150 mm

**Sample grade/Age** : M30 / 28 Days Compressive Strength

**Reference to BIS codes** : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

**Date of test** : 26/08/2020

| Sl. No. | Identification Mark | Grade of concrete | Date of Casting | Date of Testing | Dimension of the Specimen (mm) | Cross sectional area (Sq.mm) | Weight of the sample (kg) | Failure Load (KN) | Compressive strength ($N/mm^2$) | Average Compressive Strength ($N/mm^2$) |
|---|---|---|---|---|---|---|---|---|---|---|
| 1 | Cement Concrete Pavement | M30 | 29/07/2020 | 26/08/2020 | 149.63 X 151.32 X 150.58 | 22641 | 8.571 | 747.3 | 33.0 | 32.8 |
| 2 | Cement Concrete Pavement | M30 | 29/07/2020 | 26/08/2020 | 151.48 X 149.78 X 150.18 | 22689 | 8.375 | 733.3 | 32.3 | |
| 3 | Cement Concrete Pavement | M30 | 29/07/2020 | 26/08/2020 | 150.61 X 150.84 X 149.22 | 22717 | 8.433 | 752.7 | 33.1 | |

* The results obtained are satisfactory as per standard requirements.

**Note:**

The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 30 days from the date of issue of test certificate

Suresh. NK
AE W10

Page 1/1
****End of Report****

CIVIL PRO Sig Date BANGALORE

**FOR CIVIL Pro.**
R. Rudraprasad
**R RUDRAPRASAD**
Authorized Signatory
**Technical Manager**

Format No: CP/TF/01

# TEST REPORT OF CEMENT CONCRETE CUBES

**Lab ID** : **CP-2021-01-13-45** **Date: 06/08/2020**

**Customer** : Assistant Executive Engineer, Vidyaranyapura Sub Division, BBMP, Bangalore.

**Address** : Vidyaranyapura Sub Division, BBMP, Bangalore.

**Project Name** : "Improvements to Roads and Drains at G Krishna Murty Layout Mutturayaswamy Layout G K Muniyappa Garden in Ward No 10 Doddabommasandra Vidyaranyapura Sub Division."

**Agency** : Sri.Abbu Sambasiva Reddy, No: 1B3, Sree Arcade Layout, 4th Block Doddabommasandra, Vidyaranyapura Post, Bangalore-97.

**Customer's Reference** : BBMP/EE/BTP/WO/45/2020-21

**Source of Sample** : Sample supplied by Agency

**Sample Condition** : Satisfactory

**Date of Receipt** : 01-08-20

**Customer ID** : Cement Concrete Pavement

**Sample Type /Size** : 150X150X150 mm

**Sample grade/Age** : M30 / 7 Days Compressive Strength

**Reference to BIS codes** : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

**Date of test** : 06/08/2020

| Sl. No. | Identification Mark | Grade of concrete | Date of Casting | Date of Testing | Dimension of the Specimen (mm) | Cross sectional area (Sq.mm) | Weight of the sample (kg) | Failure Load (KN) | Compressive strength ($N/mm^2$) | Average Compressive Strength ($N/mm^2$) |
|---|---|---|---|---|---|---|---|---|---|---|
| 1 | Cement Concrete Pavement | M30 | 30/07/2020 | 06/08/2020 | 151.84 X 149.72 X 150.92 | 22733 | 8.998 | 585.6 | 25.8 | 25.8 |
| 2 | Cement Concrete Pavement | M30 | 30/07/2020 | 06/08/2020 | 150.22 X 150.69 X 149.10 | 22637 | 8.488 | 606.3 | 26.8 | |
| 3 | Cement Concrete Pavement | M30 | 30/07/2020 | 06/08/2020 | 150.08 X 150.73 X 150.03 | 22620 | 8.245 | 559.6 | 24.7 | |

* The results obtained are satisfactory as per standard requirements.

**Note:**

The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 30 days from the date of issue of test certificate

Suvitha. N.L
AE L10

CIVIL PRO Sig Date BANGALORE

FOR CIVIL Pro.
R RUDRAPRASAD
Authorized Signatory
Technical Manager


****End of Report****

Format No: CP/TF/01

# TEST REPORT OF CEMENT CONCRETE CUBES

**Lab ID** : **CP-2021-01-13-45** **Date: 27/08/2020**

**Customer** : Assistant Executive Engineer, Vidyaranyapura Sub Division, BBMP, Bangalore.

**Address** : Vidyaranyapura Sub Division, BBMP, Bangalore.

**Project Name** : "Improvements to Roads and Drains at G Krishna Murty Layout Mutturayaswamy Layout G K Muniyappa Garden in Ward No 10 Doddabommasandra Vidyaranyapura Sub Division."

**Agency** : Sri.Abbu Sambasiva Reddy, No: 1B3, Sree Arcade Layout, 4th Block Doddabommasandra, Vidyaranyapura Post, Bangalore-97.

**Customer's Reference** : BBMP/EE/BTP/WO/45/2020-21

**Source of Sample** : Sample supplied by Agency

**Sample Condition** : Satisfactory

**Date of Receipt** : 01-08-20

**Customer ID** : Cement Concrete Pavement

**Sample Type /Size** : 150X150X150 mm

**Sample grade/Age** : M30 / 28 Days Compressive Strength

**Reference to BIS codes** : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

**Date of test** : 27/08/2020

| Sl. No. | Identification Mark | Grade of concrete | Date of Casting | Date of Testing | Dimension of the Specimen (mm) | Cross sectional area (Sq.mm) | Weight of the sample (kg) | Failure Load (KN) | Compressive strength ($N/mm^2$) | Average Compressive Strength ($N/mm^2$) |
|---|---|---|---|---|---|---|---|---|---|---|
| 1 | Cement Concrete Pavement | M30 | 30/07/2020 | 27/08/2020 | 149.82 X 150.96 X 150.29 | 22617 | **8.571** | 751.3 | 33.2 | 32.9 |
| 2 | Cement Concrete Pavement | M30 | 30/07/2020 | 27/08/2020 | 150.63 X 149.03 X 150.19 | 22448 | **8.375** | 721.6 | 32.1 | |
| 3 | Cement Concrete Pavement | M30 | 30/07/2020 | 27/08/2020 | 149.94 X 150.96 X 151.50 | 22635 | **8.433** | 754.3 | 33.3 | |

* The results obtained are satisfactory as per standard requirements.

**Note:**

The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 30 days from the date of issue of test certificate

Suvitha. N.K
AE 010

Page 1/1
****End of Report****

CIVIL Pro Sig. Date. BANGALORE

FOR CIVIL Pro.
R RUDRAPRASAD
Authorized Signatory
**Technical Manager**

Format No: CP/TF/01

# TEST REPORT OF CEMENT CONCRETE CUBES

**Lab ID** : **CP-2021-01-13-45** **Date: 05/08/2020**

**Customer** : Assistant Executive Engineer, Vidyaranyapura Sub Division, BBMP, Bangalore.

**Address** : Vidyaranyapura Sub Division, BBMP, Bangalore.

**Project Name** : "Improvements to Roads and Drains at G Krishna Murty Layout Mutturayaswamy Layout G K Muniyappa Garden in Ward No 10 Doddabommasandra Vidyaranyapura Sub Division."

**Agency** : Sri.Abbu Sambasiva Reddy, No: 1B3, Sree Arcade Layout, 4th Block Doddabommasandra, Vidyaranyapura Post, Bangalore-97.

**Customer's Reference** : BBMP/EE/BTP/WO/45/2020-21

**Source of Sample** : Sample supplied by Agency

**Sample Condition** : Satisfactory

**Date of Receipt** : 31-07-20

**Customer ID** : Cement Concrete Pavement

**Sample Type /Size** : 150X150X150 mm

**Sample grade/Age** : M30 / 7 Days Compressive Strength

**Reference to BIS codes** : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

**Date of test** : 05/08/2020

| Sl. No. | Identification Mark | Grade of concrete | Date of Casting | Date of Testing | Dimension of the Specimen (mm) | Cross sectional area (Sq.mm) | Weight of the sample (kg) | Failure Load (KN) | Compressive strength ($N/mm^2$) | Average Compressive Strength ($N/mm^2$) |
|---|---|---|---|---|---|---|---|---|---|---|
| 1 | Cement Concrete Pavement | M30 | 29/07/2020 | 05/08/2020 | 151.31 X 150.80 X 150.08 | 22817 | **8.998** | 590.7 | 25.9 | 25.7 |
| 2 | Cement Concrete Pavement | M30 | 29/07/2020 | 05/08/2020 | 149.03 X 151.74 X 149.98 | 22615 | **8.488** | 598.3 | 26.5 | |
| 3 | Cement Concrete Pavement | M30 | 29/07/2020 | 05/08/2020 | 150.43 X 150.50 X 150.34 | 22640 | **8.245** | 557.6 | 24.6 | |

* The results obtained are satisfactory as per standard requirements.

**Note:**

The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 30 days from the date of issue of test certificate

Suvetha. NL
AE-W10

CIVIL PRO BANGALORE Sig. Date

**FOR CIVIL Pro.**

**R RUDRAPRASAD**
Authorized Signatory
**Technical Manager**


****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL |
GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES |

Format No: CP/TF/01

# TEST REPORT OF CEMENT CONCRETE CUBES

**Lab ID** : **CP-2021-01-13-45** **Date: 26/08/2020**

**Customer** : Assistant Executive Engineer, Vidyaranyapura Sub Division, BBMP, Bangalore.

**Address** : Vidyaranyapura Sub Division, BBMP, Bangalore.

**Project Name** : "Improvements to Roads and Drains at G Krishna Murty Layout Mutturayaswamy Layout G K Muniyappa Garden in Ward No 10 Doddabommasandra Vidyaranyapura Sub Division."

**Agency** : Sri.Abbu Sambasiva Reddy, No: 1B3, Sree Arcade Layout, 4th Block Doddabommasandra, Vidyaranyapura Post, Bangalore-97.

**Customer's Reference** : BBMP/EE/BTP/WO/45/2020-21

**Source of Sample** : Sample supplied by Agency

**Sample Condition** : Satisfactory

**Date of Receipt** : 31-07-20

**Customer ID** : Cement Concrete Pavement

**Sample Type /Size** : 150X150X150 mm

**Sample grade/Age** : M30 / 28 Days Compressive Strength

**Reference to BIS codes** : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

**Date of test** : 26/08/2020

| Sl. No. | Identification Mark | Grade of concrete | Date of Casting | Date of Testing | Dimension of the Specimen (mm) | Cross sectional area (Sq.mm) | Weight of the sample (kg) | Failure Load (KN) | Compressive strength ($N/mm^2$) | Average Compressive Strength ($N/mm^2$) |
|---|---|---|---|---|---|---|---|---|---|---|
| 1 | Cement Concrete Pavement | M30 | 29/07/2020 | 26/08/2020 | 149.85 X 151.42 X 150.96 | 22690 | **8.571** | 760.2 | 33.5 | 33.1 |
| 2 | Cement Concrete Pavement | M30 | 29/07/2020 | 26/08/2020 | 149.52 X 151.10 X 151.94 | 22593 | **8.375** | 740.9 | 32.8 | |
| 3 | Cement Concrete Pavement | M30 | 29/07/2020 | 26/08/2020 | 151.05 X 150.31 X 149.17 | 22704 | **8.433** | 752.7 | 33.2 | |

* The results obtained are satisfactory as per standard requirements.

**Note:**

The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 30 days from the date of issue of test certificate

Suvitha.NK
AE W10

CIVIL PRO BANGALORE Sig. Date.

**FOR CIVIL Pro.**
**R RUDRAPRASAD**
Authorized Signatory
**Technical Manager**


****End of Report****

CIVIL PRO
AN ISO 9001 : 2008 COMPANY &NABL ACCREDITED LABORATORY AS PER ISO/IEC 17025:2005
# 4, 7TH MAIN MALLESWARAM, BANGALORE -3
Certificate No.: TC-5548

Format No: CP/TF/01

# TEST REPORT OF CEMENT CONCRETE CUBES

**Lab ID** : **CP-2021-01-13-45** **Date: 05/08/2020**

**Customer** : Assistant Executive Engineer, Vidyaranyapura Sub Division, BBMP, Bangalore.

**Address** : Vidyaranyapura Sub Division, BBMP, Bangalore.

**Project Name** : "Improvements to Roads and Drains at G Krishna Murty Layout Mutturayaswamy Layout G K Muniyappa Garden in Ward No 10 Doddabommasandra Vidyaranyapura Sub Division."

**Agency** : Sri.Abbu Sambasiva Reddy, No: 1B3, Sree Arcade Layout, 4th Block Doddabommasandra, Vidyaranyapura Post, Bangalore-97.

**Customer's Reference** : BBMP/EE/BTP/WO/45/2020-21

**Source of Sample** : Sample supplied by Agency

**Sample Condition** : Satisfactory

**Date of Receipt** : 31-07-20

**Customer ID** : Cement Concrete Pavement

**Sample Type /Size** : 150X150X150 mm

**Sample grade/Age** : M30 / 7 Days Compressive Strength

**Reference to BIS codes** : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

**Date of test** : 05/08/2020

| Sl. No. | Identification Mark | Grade of concrete | Date of Casting | Date of Testing | Dimension of the Specimen (mm) | Cross sectional area (Sq.mm) | Weight of the sample (kg) | Failure Load (KN) | Compressive strength ($N/mm^2$) | Average Compressive Strength ($N/mm^2$) |
|---|---|---|---|---|---|---|---|---|---|---|
| 1 | Cement Concrete Pavement | M30 | 29/07/2020 | 05/08/2020 | 151.67 X 149.50 X 149.08 | 22675 | **8.998** | 579.4 | 25.6 | 25.5 |
| 2 | Cement Concrete Pavement | M30 | 29/07/2020 | 05/08/2020 | 150.03 X 149.91 X 151.00 | 22491 | **8.488** | 587.2 | 26.1 | |
| 3 | Cement Concrete Pavement | M30 | 29/07/2020 | 05/08/2020 | 150.55 X 150.81 X 150.30 | 22704 | **8.245** | 563.7 | 24.8 | |

* The results obtained are satisfactory as per standard requirements.

**Note:**

The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 30 days from the date of issue of test certificate

Suvitha. N.K
AE W10

CIVIL Pro. Sig. Date. BANGALORE

FOR CIVIL Pro.
R. Rudraprasad
**R RUDRAPRASAD**
Authorized Signatory
**Technical Manager**


****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL | GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES |

Format No: CP/TF/01

# TEST REPORT OF CEMENT CONCRETE CUBES

**Lab ID** : **CP-2021-01-13-45** **Date: 26/08/2020**

**Customer** : Assistant Executive Engineer, Vidyaranyapura Sub Division, BBMP, Bangalore.

**Address** : Vidyaranyapura Sub Division, BBMP, Bangalore.

**Project Name** : "Improvements to Roads and Drains at G Krishna Murty Layout Mutturayaswamy Layout G K Muniyappa Garden in Ward No 10 Doddabommasandra Vidyaranyapura Sub Division."

**Agency** : Sri.Abbu Sambasiva Reddy, No: 1B3, Sree Arcade Layout, 4th Block Doddabommasandra, Vidyaranyapura Post, Bangalore-97.

**Customer's Reference** : BBMP/EE/BTP/WO/45/2020-21

**Source of Sample** : Sample supplied by Agency

**Sample Condition** : Satisfactory

**Date of Receipt** : 31-07-20

**Customer ID** : Cement Concrete Pavement

**Sample Type /Size** : 150X150X150 mm

**Sample grade/Age** : M30 / 28 Days Compressive Strength

**Reference to BIS codes** : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

**Date of test** : 26/08/2020

| Sl. No. | Identification Mark | Grade of concrete | Date of Casting | Date of Testing | Dimension of the Specimen (mm) | Cross sectional area (Sq.mm) | Weight of the sample (kg) | Failure Load (KN) | Compressive strength ($N/mm^2$) | Average Compressive Strength ($N/mm^2$) |
|---|---|---|---|---|---|---|---|---|---|---|
| 1 | Cement Concrete Pavement | M30 | 29/07/2020 | 26/08/2020 | 151.73 X 150.60 X 149.01 | 22850 | **8.571** | 769.8 | 33.7 | 33.2 |
| 2 | Cement Concrete Pavement | M30 | 29/07/2020 | 26/08/2020 | 149.11 X 151.12 X 150.53 | 22533 | **8.375** | 738.1 | 32.8 | |
| 3 | Cement Concrete Pavement | M30 | 29/07/2020 | 26/08/2020 | 151.33 X 150.88 X 150.82 | 22832 | **8.433** | 759.9 | 33.3 | |

* The results obtained are satisfactory as per standard requirements.

**Note:**

The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 30 days from the date of issue of test certificate

Sweetha. N K
AE W 10

CIVIL PRO Sig. Date.

**FOR CIVIL Pro.**

**R RUDRAPRASAD**
Authorized Signatory
**Technical Manager**


****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL | GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES |

Format No: CP/TF/01

# TEST REPORT OF CEMENT CONCRETE CUBES

**Lab ID** : **CP-2021-01-13-45** **Date: 06/08/2020**

**Customer** : Assistant Executive Engineer, Vidyaranyapura Sub Division, BBMP, Bangalore.

**Address** : Vidyaranyapura Sub Division, BBMP, Bangalore.

**Project Name** : "Improvements to Roads and Drains at G Krishna Murty Layout Mutturayaswamy Layout G K Muniyappa Garden in Ward No 10 Doddabommasandra Vidyaranyapura Sub Division."

**Agency** : Sri.Abbu Sambasiva Reddy, No: 1B3, Sree Arcade Layout, 4th Block Doddabommasandra, Vidyaranyapura Post, Bangalore-97.

**Customer's Reference** : BBMP/EE/BTP/WO/45/2020-21

**Source of Sample** : Sample supplied by Agency

**Sample Condition** : Satisfactory

**Date of Receipt** : 01-08-20

**Customer ID** : Cement Concrete Pavement

**Sample Type /Size** : 150X150X150 mm

**Sample grade/Age** : M30 / 7 Days Compressive Strength

**Reference to BIS codes** : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

**Date of test** : 06/08/2020

| Sl. No. | Identification Mark | Grade of concrete | Date of Casting | Date of Testing | Dimension of the Specimen (mm) | Cross sectional area (Sq.mm) | Weight of the sample (kg) | Failure Load (KN) | Compressive strength ($N/mm^2$) | Average Compressive Strength ($N/mm^2$) |
|---|---|---|---|---|---|---|---|---|---|---|
| 1 | Cement Concrete Pavement | M30 | 30/07/2020 | 06/08/2020 | 149.71 X 150.58 X 151.92 | 22544 | **8.998** | 575.9 | 25.5 | 25.4 |
| 2 | Cement Concrete Pavement | M30 | 30/07/2020 | 06/08/2020 | 151.10 X 150.91 X 151.35 | 22802 | **8.488** | 598.3 | 26.2 | |
| 3 | Cement Concrete Pavement | M30 | 30/07/2020 | 06/08/2020 | 151.82 X 150.67 X 151.72 | 22875 | **8.245** | 559.8 | 24.5 | |

* The results obtained are satisfactory as per standard requirements.

**Note:**

The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 30 days from the date of issue of test certificate

Suvitha. N.L
AE Lab

**FOR CIVIL Pro.**

**R RUDRAPRASAD**
Authorized Signatory
**Technical Manager**

CIVIL PRO BANGALORE Sig. Date


****End of Report****

Format No: CP/TF/01

# TEST REPORT OF CEMENT CONCRETE CUBES

**Lab ID** : **CP-2021-01-13-45** **Date: 27/08/2020**

**Customer** : Assistant Executive Engineer, Vidyaranyapura Sub Division, BBMP, Bangalore.

**Address** : Vidyaranyapura Sub Division, BBMP, Bangalore.

**Project Name** : "Improvements to Roads and Drains at G Krishna Murty Layout Mutturayaswamy Layout G K Muniyappa Garden in Ward No 10 Doddabommasandra Vidyaranyapura Sub Division."

**Agency** : Sri.Abbu Sambasiva Reddy, No: 1B3, Sree Arcade Layout, 4th Block Doddabommasandra, Vidyaranyapura Post, Bangalore-97.

**Customer's Reference** : BBMP/EE/BTP/WO/45/2020-21

**Source of Sample** : Sample supplied by Agency

**Sample Condition** : Satisfactory

**Date of Receipt** : 01-08-20

**Customer ID** : Cement Concrete Pavement

**Sample Type /Size** : 150X150X150 mm

**Sample grade/Age** : M30 / 28 Days Compressive Strength

**Reference to BIS codes** : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

**Date of test** : 27/08/2020

| Sl. No. | Identification Mark | Grade of concrete | Date of Casting | Date of Testing | Dimension of the Specimen (mm) | Cross sectional area (Sq.mm) | Weight of the sample (kg) | Failure Load (KN) | Compressive strength ($N/mm^2$) | Average Compressive Strength ($N/mm^2$) |
|---|---|---|---|---|---|---|---|---|---|---|
| 1 | Cement Concrete Pavement | M30 | 30/07/2020 | 27/08/2020 | 151.24 X 151.41 X 150.19 | 22900 | **8.571** | 771.5 | 33.7 | 33.2 |
| 2 | Cement Concrete Pavement | M30 | 30/07/2020 | 27/08/2020 | 151.32 X 149.73 X 151.14 | 22657 | **8.375** | 731.0 | 32.3 | |
| 3 | Cement Concrete Pavement | M30 | 30/07/2020 | 27/08/2020 | 150.99 X 150.14 X 149.73 | 22671 | **8.433** | 759.9 | 33.5 | |

* The results obtained are satisfactory as per standard requirements.

**Note:**

The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 30 days from the date of issue of test certificate

Sweetha. N K
AE W10

Page 1/1
****End of Report****

CIVIL Pro Sig Date BANGALORE

FOR CIVIL Pro.
R RUDRAPRASAD
Authorized Signatory
Technical Manager